
TECHNICAL DATA SHEET

PRODUCT **WAYSIDE M.S. POLYMER® ADHESIVE & SEALANT**

DESCRIPTION

Wayside M.S.Polymer® adhesive & sealant is a one part, solvent-free adhesive based on the latest polymer technology. It has excellent UV resistance and primerless adhesion to most substrates. It cures to a tough, elastic adhesive sealant with applications across a range of industries. The cured sealant has good abrasion, oil and solvent resistance.

APPLICATION

Construction uses include perimeter sealing of plastic, timber and metal frames along with the sealing of expansion and construction joints; it may be used on moist surfaces.

The product is also suitable for many applications within the automotive, Roofing, marine and coachwork industries.

Suitable for sealing and bonding connection joints in ducting, ventilation and air conditioning installations.

LIMITATIONS

Wayside M.S. Polymer® Sealants should not be used to seal aquariums. Submerged joints need special attention to surface preparation and application and should be checked for integrity at regular intervals.

Always check to determine suitability of the sealant on any surface that may give cause for concern.

TECHNICAL DETAILS

Cure system:	Cures by vulcanization upon exposure to moisture in atmosphere.
Specific Gravity:	Colours: 1.48-1.52; Translucent: 1.03-1.07
Skimming time:	approx. 45 minutes (at 23°C and 50% relative humidity).
Cure rate:	Approx 3mm per 24Hrs (at 23°C and 50% relative humidity). As the joint depth increases, the cure rate will slow down.
Shore A hardness:	approx. 50 -55
Tensile Strength (100%):	0.9 MPa
Movement accommodation:	±20%
Application Temp Range:	+5°C to +35°C.
Service Temp Range:	-40°C to +100°C.

Shelf Life: Minimum 9 months when stored in unopened cartridges under cool, dry conditions.

Life Expectancy: When used and applied correctly the sealant will perform in excess of 20 years.

APPLICATION INSTRUCTIONS

Surfaces to which Sealant is to adhere must be clean and free from loose material, standing water or contaminants which otherwise may impair the bond. Non-porous surfaces such as aluminium should be cleaned with a suitable product. It may be necessary to prime some porous surfaces depending on cohesiveness and porosity of the substrate. For application where some movement will be exhibited i.e. construction joints, the minimum joint dimensions should be 6mm x 6mm with the maximum dimensions being 20mm wide by 12mm deep. Where deeper joints are found, depth can be reduced using a suitable backer rod. Areas of perimeter pointing where a fillet is to be applied, the minimum measurement across must be 10mm with a minimum depth of 6mm. If conditions are suitable for application ensure joints are properly prepared, and apply sealant firmly into the joint using an application gun. Ensure a good solid fill is achieved. Once applied, sealant can be tooled within 10 minutes to required finish.

The cured sealant can be painted if required, but is not necessary. Painting sealant in a movement joint is not recommended as the movement of the sealant may be greater than the flexibility of the paint, leading to cracking or crazing of the paint film.

COVERAGE

1 std size cartridge is sufficient to seal approximately 10m with a 6mm bead.

Also available in a 600ml foil pack

COLOURS

White, Grey, Black, Grass Green and Translucent as standard and other colours on request

STORAGE

Store in dry conditions between 5°C and 25°C.

HEALTH AND SAFETY

Consult Health and Safety Data Sheet.

Avoid contact of uncured sealant with the skin. If uncured sealant comes into contact with eyes, flush out immediately with clean water for at least 5 minutes. Consult medical advise if irritation persists

Use in a well ventilated area.

As with all chemical products, care should be taken during use and storage.

Do not eat or drink while using the product.

Keep away from children and animals.

Further Information

These data are offered in good faith as typical values and not as a product specification. No warranty, either expressed or implied, is hereby made. The recommended industrial hygiene and safe handling procedures are believed to be generally applicable, each user should review these recommendations in the specific context of the intended use and determine whether they are appropriate

ISSUE 2: February 2016